Hawleys CITE ST CITE ST Edition

BEST AVAILABLE COPY

Exhibit 2

Copyright © 1987 by Van Nostrand Reinhold Company Inc.

Library of Congress Catalog Card Number: 86-23333 ISBN: 0-442-28097-1

All rights reserved. Certain portions of this work copyright © 1930, 1920, 1919 by The Chemical Catalog Co., Inc. and 1981, 1977, 1971, 1966, 1956, 1950 by Van Nostrand Reinhold Company Inc. No part of this work covered by the copyright hereon may be reproduced or used in any form or by any means—graphic, electronic, or mechanical, including photocopying, recording, taping, or information storage and retrieval systems—without permission of the publisher.

Printed in the United States of America

Van Nostrand Reinhold Company Inc. 115 Fifth Avenue New York, New York 10003

Van Nostrand Reinhold Company Limited Molly Millars Lane Wokingham, Berkshire RG11 2PY, England

Van Nostrand Reinhold 480 Latrobe Street Melbourne, Victoria 3000, Australia

Macmillan of Canada Division of Canada Publishing Corporation 164 Commander Boulevard Agincourt, Ontario M1S 3C7, Canada

15 14 13 12 11 10 9 8 7 6 5 4 3 2 1

Library of Congress Cataloging-in-Publication Data

Condensed chemical dictionary.

Hawley's condensed chemical dictionary.

Rev. ed. of: The Condensed chemical dictionary.

10th ed./rev. by Gessner G. Hawley, 1981.

1. Chemistry—Dictionaries. I. Hawley, Gessner
Goodrich, 1905— II. Sax, N. Irving (Newton Irving)

III. Lewis, Richard J., Sr. IV. Title.

QD5.C5 1987 540'.3'21 86-23333

ISBN 0-442-28097-1

hydrometer. Device for measuring the density of liquids. See also Baume'

hydronium ion. An ion (H₃O+) formed by the transfer of a proton (hydrogen nucleus) from one molecule of water to another, a companion ion (OH·) is also formed, the reaction is 2HOH → H₃O⁺ + OH-. Formation of such ions is statistically rare, resulting from the interaction of water molecules in a ratio of 1:556 million.

hydroperoxide. An organic peroxide having the generalized formula ROOH. An example is ethyl hydroperoxide (C₂H₅OOH). Methyl and ethyl hydroperoxides are unstable and thus are strong oxidizing agents and explosion hazards; those of higher molecular weight are more stable. Hydroperoxides can be derived by oxidation of saturated hydrocarbons, or by alkylating hydrogen peroxide in a strongly acidic environment. They are used as polymerization initiators.

hydrophilic. Having a strong tendency to bind or absorb water, which results in swelling and formation of reversible gels. This property is characteristic of carbohydrates, such as algin, vegetable gums, pectins and starches, and of complex proteins such as gelatin and collagen.

hydrophobic. Antagonistic to water, incapable of dissolving in water. This property is characteristic of all oils, fats, waxes, and many resins, as well as of finely divided powders like carbon black and magnesium carbonate.

hydroponics. See nutrient solution.

"Hydro-Pruf."300 TM for a silicone water repellent for fabrics. Applied with a catalyst at high curing temperatures.

hydroquinol. See hydroquinone.

hydroquinone. (quinol; hydroquinol; p-dihy-CAS: 123-31-9. droxybenzene). C₆H₄(OH)₂.

Properties: White crystals; soluble in water, alcohol, and ether; d 1.330; mp 170C; bp 285C; flash 329F (165C); autoign temperature 960F (515.5C). Combustible.

Derivation: Aniline is oxidized to quinone by manganese dioxide and is then reduced to hydroquinone.

Grade: Technical, photographic.

Hazard: Toxic by ingestion and inhalation, irri-

tant. TLV: 2 mg/m3 of air.

Use: Photographic developer (except color film); dye intermediate; inhibitor; stabilizer in paints and varnishes, motor fuels, and oils; antioxidant for fats and oils; inhibitor of polymerization.

hydroquinone benzyl ether. See p-benzyloxyphenol.

hydroquinone dibenzyl ether. CAS: 103-16-2. C₆H₅CH₂OC₆H₄OCH₂C₆H₅.

Properties: Tan powder; mp 119C (min); purity 90% (min); insoluble in water; soluble in acetone, benzene, and chlorobenzene. Combustible. Use: Solvent; perfumes, soap, plastics, and pharmaceuticals.

hydroquinone di-n-butyl ether. (1,4-dibutoxy- $C_6H_4[O(CH_2)_3CH_3]_2$. benzene).

Properties: White flakes with no appreciable odor; mp 45-46C; bp 124C (1.3 mm), 158C (15.0 mm); insoluble in water; soluble in benzene, acetone, ethyl acetate, and alcohol. Combustible.

hydroquinone diethyl ether. (1,4-diethoxyben- $C_6H_4(OC_2H_5)_2$. zene).

Properties: White granular solid with anise-like odor, mp 71-72C, bp 246C. Neither boiling caustic nor acid solution cause any hydrolysis. Absorbs UV light. Insoluble in water; soluble in benzene, acetone, ethyl acetate, and alcohol. Combustible.

hydroquinone di($oldsymbol{eta}$ -hydroxyethyl) ether. (p-di-[2-hydroxyethoxy]benzene). C₆H₄(OC₂H₄OH)₂.

Properties: White solid, mp 99C, bp 185-200C (0.3 mm), slightly soluble in water and most organic solvents, miscible with water at 80C. Combustible.

Use: Preparation of polyester, polyolefins, polyurethanes and hard waxy resins, organic synthe-

hydroquinone dimethyl ether. (1,4-dimethoxybenzene; DMB; dimethyl hydroquinone). C₆H₄(OCH₃)₂. CAS: 654-42-2.

Properties: White flakes with sweet clover odor, bp 213C, mp 56C, d 1.0293 (65C), viscosity 1.04